



PREALPINA
T A N N E R Y

GOMMA

Characteristics

Ox sides European Origin (Bos Taurus)
Size 1.5-2.0 square meter / Chrome tanned
Through-dyeing Aniline
Pigmented finishing
Thickness 1.1/1.3 mm

Technical characteristics

Dry rub fastness
(UNI EN ISO 11640) 500 cycles >3 grey scale
Wet rub fastness
(UNI EN ISO 11640) 100 cycles >3 grey scale
Alkaline solution rub fastness
(UNI EN ISO 11640) 80 cycles >3 grey scale
Adhesion of finishing
(UNI EN ISO 11644) >2N/cm
Flexing resistance
(UNI EN ISO 5402) 50.000 cycles No cracks
Flexing resistance - Humid
(UNI EN ISO 5402) 10.000 cycles No cracks

Chemical characteristics

The article meets the Reach requirements.

Cleaning and maintenance

- avoid direct exposure to the sunlight
- keep away from heat sources
- clean with damp cloth dry immediately