



PREALPINA
T A N N E R Y

LONDON

Characteristics

Bovine sides European Origin (Bos Taurus)

Size 1.8-2.0 square meter

Chrome tanned / Through-dyeing Aniline

Thickness available from 1.2 to 1.6 mm

Technical characteristics

Dry rub fastness

(UNI EN ISO 11640) 200 cycles >3 grey scale

Wet rub fastness

(UNI EN ISO 11640) 100 cycles >3 grey scale

Alkaline solution rub fastness

(UNI EN ISO 11640) 50 cycles >3 grey scale

Adhesion of finishing

(UNI EN ISO 11644) >2N/cm

Flexing resistance

(UNI EN ISO 5402) 50.000 cycles No cracks

Flexing resistance - Humid

(UNI EN ISO 5402) 10.000 cycles No cracks

Chemical characteristics

The article meets the Reach requirements

Cleaning and maintenance

- avoid direct exposure to the sunlight
- keep away from heat sources