

TECHNICAL DATA SHEET

Article: ***ALCE***

Thickness: 1.4 – 1.6 mm

Origin: Bovine

Type of tanning: Mineral, based on Chromium salt

Type of finishing: Semi Aniline

Appearance: Semi glossy and tumbled

<i>PHYSICAL / MECHANICAL PROPERTIES</i>		
Characteristic	Test Method	Value
Tensile Strength	UNI EN ISO 3376	$\geq 10 \text{ N/mm}^2$
Percentage Extension	UNI EN ISO 3376	$> 20\%$
Tear Load	UNI EN ISO 3377-2	$\geq 60 \text{ N}$
Distension and strength of surface (Ball burst method)	UNI EN ISO 3379	$\geq 7,0 \text{ mm}$
Dry Adhesion of finishing	UNI EN ISO 11644	$\geq 2 \text{ N/10 mm}$
Dry Flex Resistance	UNI EN ISO 5402-1	50000 cycles: No damages
Wet Flex Resistance	UNI EN ISO 5402-1	10000 cycles: No damages
<i>COLOUR FASTNESS TESTS</i>		
Characteristic	Test Method	Value
Dry Rub Fastness	UNI EN ISO 11640	100 cycles ≥ 3 grey scale
Wet Rub Fastness	UNI EN ISO 11640	20 cycles ≥ 3 grey scale