



**PREALPINA**  
T A N N E R Y



## TECHNICAL DATA SHEET

**Article:** ***WILD***

**Thickness:** 1.2 - 1.4 mm

**Origin:** Bovine

**Type of tanning:** Mineral, based on Chromium salt

**Type of finishing:** Semi aniline

**Appearance:** Semi glossy, embossed

### ***PHYSICAL / MECHANICAL PROPERTIES***

| Characteristic                                         | Test Method       | Value                                              |
|--------------------------------------------------------|-------------------|----------------------------------------------------|
| Tensile Strength                                       | UNI EN ISO 3376   | $\geq 10 \text{ N/mm}^2$                           |
| Percentage Extension                                   | UNI EN ISO 3376   | $> 20\%$                                           |
| Tear Load                                              | UNI EN ISO 3377-2 | $\geq 60 \text{ N}$                                |
| Distension and strength of surface (Ball burst method) | UNI EN ISO 3379   | $\geq 7,0 \text{ mm}$                              |
| Dry Flex Resistance                                    | UNI EN ISO 5402-1 | 50000 cycles: No damages                           |
| Wet Flex Resistance                                    | UNI EN ISO 5402-1 | 10000 cycles: No damages                           |
| Martindale Abrasion Resistance                         | UNI EN 13520      | 3200 dry cycles: No worse than a moderate abrasion |

### ***COLOUR FASTNESS TESTS***

|                                               |                  |                                |
|-----------------------------------------------|------------------|--------------------------------|
| Dry Rub Fastness                              | UNI EN ISO 11640 | 100 cycles $\geq 3$ grey scale |
| Wet Rub Fastness                              | UNI EN ISO 11640 | 20 cycles $\geq 3$ grey scale  |
| Colour Fastness to PVC Migration (Grain Side) | UNI EN ISO 15701 | $\geq 3$ grey scale            |